


UK System 	Water based finishing system for Medite Tricoya Extreme
	Dulux Trade Weathershield Quick Drying Exterior Gloss / Satin

Surface Substrate:	Medite Tricoya Extreme	Required Finish Coat:	Dulux Trade Weathershield Quick Drying Exterior Gloss / Satin
Previous Coating:	None / New board	Finish Coat Data Sheet:	428 / 421
Surface Condition:	Good (new uncoated)	Finish Coat Colour Reference:	See Colour Schedule
Durability Performance:	High	No. of Finish System Coats:	3
Finish Type:	Water-based		
Sheen:	Satin / Gloss		
Brand:	Dulux		

- Comply at all times with BS 6150: 2006 Code of Practice for Painting of Buildings (or as amended) and BS EN ISO 12944: 1998 Paints and Varnishes - Corrosion Protection of Steel Structures by Protective Paint Systems (or as amended).
- AkzoNobel Decorative Paints will not accept responsibility for any unauthorised amendments or usage of the wording contained in this System sheet and in Paint's Site Work Instructions v5.
- In order to achieve the optimum results, it is extremely important to adhere to the systems and AkzoNobel Decorative Paint's Site Work Instructions v5 quoted.
- Products supplied for the carrying out of this specification are compliant with Statutory Instrument 2005 No. 2773 (Environmental Protection) - The Volatile Organic Compounds in Paints, Varnishes and Vehicle Refinishing Products Regulations 2005.

Preparation

Thoroughly clean down to ensure all areas are free from dirt, grease and surface contaminants. Remove oils from surface by wiping with a sharp solvent. Round all sharp edges (a radius of 1 mm to 2 mm for timber other than sills and thresholds; 3mm for sills and thresholds) and *dust off. Ensure all surfaces are fully dry before proceeding. Note *When rubbing down dry and/or dusting off wear a suitable face mask to avoid the inhalation of dust. (See ICI Trade Paints Site Work Instructions v5 Clause SW4.20 for further information.)

Priming

2 coats of Dulux Trade Weathershield Preservative Primer+(BP)

LIBERALLY APPLY 2 coat of Dulux Trade Weathershield Preservative Primer + (BP) overall.

*Caution Weathershield Preservative Primer + (BP) contains: 3-iodo-2-propynyl-n-butyl carbamate and propiconazole. Use biocides safely. Always read the label and product information before use.

Making Good

Make good all cracks, nail-holes, open joints and other imperfections with Dulux Trade Weathershield Exterior Flexible Filler. When set carefully rub down and *dust off. Fillers, Stoppers & Glazing Compounds Use only good quality/compatible materials and follow the manufacturers' recommendations for use, even if at variance with this system. Note *When rubbing down dry and/or dusting off wear a suitable face mask to avoid the inhalation of dust. (See ICI Trade Paints Site Work Instructions v5 Clause SW4.20 for further information.)

Finishing System

One coat of Dulux Trade Weathershield Quick Drying Exterior Undercoat of selected shade.

2 coats of Dulux Trade Weathershield Quick Drying Exterior Gloss or Satin of selected shade.

For a more detailed specification regarding this site practices, please see the ICI Trade Paints Site Work Instructions available from Medite Europe (www.meditetricoya.com/downloads) or from www.duspec.co.uk

For technical advice please contact 08444 817818